

Borealis PP HD234CF

Polypropylene Homopolymer

Borealis AG

Message:

HD234CF is a homopolymer film resin, suitable for the manufacturing of unoriented film on chill roll process.
HD234CF contains antiblock and slip agents.

General Information	
Additive	Antiblock (1800 ppm) 2 Slip (2000 ppm) 3
Features	Antiblocking Good Processability Heat Sterilizable High Stiffness Homopolymer Narrow Molecular Weight Distribution Opticals Slip
Uses	Film Food Packaging Laminates Non-oriented Film Packaging Stationary Supplies
Forms	Pellets
Processing Method	Cast Film Film Extrusion

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (23°C, Injection Molded)	1300	MPa	ISO 178
Coefficient of Friction (vs. Itself - Dynamic)	0.25		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus			ISO 527-3
MD : 50 µm	700	MPa	

TD : 50 µm	700	MPa	
Tensile Strength			ISO 527-3
MD : 50 µm	45.0	MPa	
TD : 50 µm	35.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 50 µm	600	%	
TD : Break, 50 µm	700	%	
Instrumented Dart Impact (50 µm, Total Energy)		J	ISO 7765-2
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	162	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Gloss (20°, 50.0 µm)	> 110		ASTM D2457
Haze (50.0 µm)	< 2.5	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

