

Polifil® PC GFPC-10

Polycarbonate

The Plastics Group

Message:

Polifil® GFPC series compounds offer a combination of improved dimensional stability and decreased flammability. The excellent balance of physical properties make the Polifil® glass-filled polycarbonate line an excellent choice for electrical, appliance, and hardware applications. Standard processing techniques are applicable. Use this information as a guide to aid you in selecting the proper resin for your application. TPG will custom compound and fine-tune our formulations for your application.

General Information			
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Features	Flame Retardant		
	Good Dimensional Stability		
Uses	Appliance Components		
	Electrical Parts		
Agency Ratings	CSA Unspecified Rating		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2860	MPa	ASTM D638
Tensile Strength (23°C)	79.3	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	3.0	%	
Break, 23°C	10	%	
Flexural Modulus - Tangent (23°C)	3930	MPa	ASTM D790
Flexural Strength (23°C)	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Gardner Impact (23°C, 12.7 mm)	0.678	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, Unannealed	143	°C
1.8 MPa, Unannealed	135	°C
Injection	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	4.0 to 5.0	hr
Rear Temperature	266 to 277	°C
Middle Temperature	271 to 282	°C
Front Temperature	277 to 293	°C
Nozzle Temperature	282 to 299	°C
Processing (Melt) Temp	277 to 304	°C
Mold Temperature	76.7 to 98.9	°C
Injection Rate	Moderate	
Back Pressure	0.172 to 0.517	MPa
Screw Speed	30 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT