

LNP™ STAT-KON™ Lexan_LCF1506

compound

Polycarbonate

SABIC Innovative Plastics

Message:

15% carbon fiber, 6% PTFE reinforced polycarbonate.

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 15% filler by weight		
Additive	PTFE lubricant (6%)		
Features	Lubrication		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage			Internal method
Flow: 3.20mm	0.050 - 0.15	%	Internal method
Transverse flow: 3.20mm	0.20 - 0.30	%	Internal method
K (wear) Factor ¹	1000		Internal method
Static Decay ²	10	msec	FTMS 101B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³			ASTM D638
Yield	111	MPa	ASTM D638
Fracture	111	MPa	ASTM D638
Tensile Elongation ⁴ (Break)	4.1	%	ASTM D638
Flexural Modulus			ASTM D790
100mm span ⁵	8420	MPa	ASTM D790
50.0mm span ⁶	9080	MPa	ASTM D790
Flexural Strength			ASTM D790
Fracture, 50.0mm span ⁷	161	MPa	ASTM D790
Fracture, 100mm span ⁸	154	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
With steel-dynamic	0.19		ASTM D1894
With steel-static	0.41		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	280	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Energy at Peak Load)	11.8	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, unannealed, 3.20mm	142	°C	ASTM D648
0.45 MPa, unannealed, 6.40mm	144	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	138	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	139	°C	ASTM D648
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
NOTE			
1.	xE-10, PV=2000 psi-fpm vs Steel		
2.	5000V to <50V		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	2.6 mm/min		
6.	1.3 mm/min		
7.	1.3 mm/min		
8.	2.6 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT