

UmaPET MHLO

Polyethylene Terephthalate

Ester Industries Ltd.

Message:

KEY FEATURES

UmaPET MHLO film is medium Haze, medium gloss film with excellent muted and grainy surface with one side chemically primed for improved adhesion performance.

The film exhibits excellent thermal, mechanical and matte surface properties along with excellent dimensional stability and excellent process ability.

After metallization, shows silver finish as aesthetic.

APPLICATIONS

The film is widely used for label face stocks, carrier for thermal transfer printing, hot stamping, paper board and carton lamination applications.

Chemical coated surface gives enhanced adhesion performance to inks, adhesives and other primer coatings and metal in metallization.

Metallized films can be used as label face stocks and sandwich barrier layer which show silver aesthetic appearance to the package in flexible packaging.

General Information			
Features	Excellent Printability		
	Good Adhesion		
	Good Dimensional Stability		
	Good Processability		
	Medium Gloss		
	Metallizable		
Uses	Coating Applications		
	Film		
	Labels		
	Laminates		
Appearance	Matte Finish		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage			ASTM D1204
Flow : 150°C, 30 min, 0.0120 mm	2.0	%	
Across Flow : 150°C, 30 min, 0.0120 mm	0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction ¹			ASTM D1894
vs. Itself - Dynamic	0.38		
vs. Itself - Static	0.45		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	12	µm	
Film Thickness - Recommended / Available	12 µm		
Tensile Strength			ASTM D882
MD : Break, 12 µm	186	MPa	
TD : Break, 12 µm	196	MPa	

Tensile Elongation			ASTM D882
MD : Break, 12 μm	90	%	
TD : Break, 12 μm	85	%	
Yield (12.0 μm)	59.5	m ² /kg	Internal Method
Wetting Tension - Coated side (12.0 μm)	48	dyne/cm	ASTM D2578
Optical	Nominal Value	Unit	Test Method
Gloss (60°)	48		ASTM D2457
Haze (12.0 μm)	44	%	ASTM D1003
NOTE			
1.	12 μm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

