

Eleme HFG00356

High Density Polyethylene
Eleme Petrochemical Company Ltd

Message:
Carry bag, grocery bags trash bags, liners, co-extrusion, etc.

General Information			
Uses	Bags		
	Film		
	Liners		
Processing Method	Coextrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.956	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	ASTM D882
Tensile Strength			
MD : Break, 25 µm	26.0	MPa	
TD : Break, 25 µm	26.0	MPa	ASTM D882
Tensile Elongation			
MD : Break, 25 µm	500	%	
TD : Break, 25 µm	800	%	ASTM D790
Flexural Modulus			
MD : 25 µm	800	MPa	
TD : 25 µm	1000	MPa	ASTM D1922
Elmendorf Tear Strength			
MD : 25 µm	0.70	g	
TD : 25 µm	25	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ASTM D1525 ¹
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

