InnoPlus LD2420H

Low Density Polyethylene

PTT Global Chemical Public Company Limited

Message:

Special Characteristics: InnoPlus LD2420H is produced by high pressure tubular process, a technology licensed by LyondellBasell. This grade offers easy processability, excellent optical property and low gel level.

Typical Applications: InnoPlus LD2420H is a very versatile of general purpose films, shrink films, food packaging films and foam applications. Additives: No additives.

| General Information | | | |
|--|---------------------|----------|-------------|
| Features | Additive Free | | |
| | General Purpose | | |
| | Good Processability | | |
| | Low Gel | | |
| | Opticals | | |
| | | | |
| Uses | Film | | |
| | Foam | | |
| | Food Packaging | | |
| | General Purpose | | |
| | Packaging | | |
| | Shrink Wrap | | |
| | | | |
| Appearance | Clear/Transparent | | |
| Processing Method | Film Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.924 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 1.9 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus (Compression Molded) | 260 | MPa | ISO 527-2 |
| Tensile Stress (Yield, Compression Molded) | 11.0 | MPa | ISO 527-2 |
| Films | Nominal Value | Unit | Test Method |
| Film Thickness - Tested | 50 | μm | |
| Tensile Stress | | | ISO 527-3 |
| MD : Break, 50 μm, Blown Film | 21.0 | MPa | |
| TD : Break, 50 µm, Blown Film | 20.0 | MPa | |
| Tensile Elongation | | | ISO 527-3 |
| MD : Break, 50 μm, Blown Film | 250 | % | |
| TD : Break, 50 µm, Blown Film | 600 | % | |
| Dart Drop Impact (50 µm, Blown Film) | 90 | g | ASTM D1709 |

| Thermal | Nominal Value | Unit | Test Method |
|----------------------------------|---------------|------|-------------|
| Vicat Softening Temperature | 93.0 | °C | ASTM D1525 |
| Melting Temperature | 111 | °C | ISO 11357-3 |
| Optical | Nominal Value | Unit | Test Method |
| Gloss (20°, 50.0 μm, Blown Film) | > 80 | | ASTM D2457 |
| Haze (50.0 μm, Blown Film) | < 8.0 | % | ASTM D1003 |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 160 to 200 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

