

Vandar® 4632Z

Polybutylene Terephthalate

Celanese Corporation

Message:

Vandar 4632Z is a high impact, 15% glass reinforced polyester alloy. It combines high strength and toughness with a moderate degree of rigidity. It is characterized by excellent solvent resistance, dimensional stability, and moldability.

General Information			
UL YellowCard	E45575-239398		
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Good dimensional stability		
	Rigid, good		
	High strength		
	Solvent resistance		
	Good formability		
	Good toughness		
RoHS Compliance	Contact manufacturer		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	7.00	cm ³ /10min	ISO 1133
Molding Shrinkage			
Flow	0.40 - 0.60	%	ASTM D955
Vertical flow direction	1.2 - 1.4	%	ISO 294-4
Flow direction	0.40 - 0.60	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	109		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield, 23°C	62.1	MPa	ASTM D638
Fracture	60.0	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	5.0	%	ASTM D638
Fracture	4.0	%	ISO 527-2/1A/5

Flexural Modulus (23°C)	3800	MPa	ISO 178
Flexural Stress (23°C)	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	18	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	62	kJ/m ²	ISO 179/1eU
23°C	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	7.0	kJ/m ²	ISO 180/1A
23°C	17	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	210	°C	ISO 75-2/B
0.45 MPa, annealed	207	°C	ASTM D648
1.8 MPa, not annealed	154	°C	ASTM D648, ISO 75-2/A
Glass Transition Temperature ¹	60.0	°C	ISO 11357-2
Vicat Softening Temperature	180	°C	ISO 306/B50
Melting Temperature ²	225	°C	ISO 11357-3, ASTM D3418
Linear thermal expansion coefficient			ISO 11359-2
Flow	2.5E-5	cm/cm/°C	ISO 11359-2
Lateral	1.4E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	ohms·cm	IEC 60093
Dielectric Strength	30	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.60		IEC 60250
1 MHz	4.10		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	7.0E-3		IEC 60250
1 MHz	0.029		IEC 60250
Comparative Tracking Index	425	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Max Regrind	25	%	
Hopper Temperature	20.0 - 50.0	°C	

Rear Temperature	230 - 240	°C
Middle Temperature	235 - 250	°C
Front Temperature	235 - 250	°C
Nozzle Temperature	240 - 260	°C
Processing (Melt) Temp	235 - 260	°C
Mold Temperature	65.0 - 96.0	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.00 - 0.345	MPa

Injection instructions

Manifold Temperature: 250 to 260°C Zone 4 Temperature: 240 to 260°C Feed Temperature: 230 to 240°C

NOTE

1. 10°C/min
2. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

