

ADDILENE H 652

Polypropylene Homopolymer
ADDIPLAST

Message:

ADDILENE H 652 is a Polypropylene Homopolymer (PP Homopolymer) material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.

Important attributes of ADDILENE H 652 are:

Good Aesthetics

Heat Resistant

High Gloss

Typical applications include:

Appliances

Electrical/Electronic Applications

Housings

Packaging

General Information			
Features	Good Surface Finish		
	High Gloss		
	High Heat Resistance		
Uses	Appliance Components		
	Cosmetic Packaging		
	Electrical/Electronic Applications		
	Housings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	28	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	74		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	35.0	MPa	
Break	33.0	MPa	
Tensile Strain (Break)	10	%	ISO 527-2
Flexural Modulus	1350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	2.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	°C	ISO 75-2/Af
Vicat Softening Temperature	150	°C	ISO 306/A50
Melting Temperature (DSC)	165	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	600	V	IEC 60112

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

