NEFTEKHIM PP 1523J (EXPPTQ)

Polypropylene Homopolymer

Nizhnekamskneftekhim Inc.

Message:

Product obtained by polymerization of propylene in presence of complex organic metal catalysts.

It incorporates increased long-term thermal stability, thermaloxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, improved rheology of melt.

Application: biaxial oriented uni- and multilayer metallized film.

Technical requirements: TU 2211-136-05766801-2006

General Information					
Features	Controlled Rheology				
	Good Thermal Stability				
	Homopolymer				
	Oxidation Resistant				
Uses	Bi-axially Oriented Film				
	Film				
	Multilayer Film				
Forms	Pellets				
Processing Method	Film Extrusion				
Physical	Nominal Value	Unit	Test Method		
Density	0.900	g/cm³			
Apparent Density	0.48 to 0.52	g/cm³			
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	2.7 to 3.3	g/10 min	ASTM D1238		
Ash Content	0.025 to 0.050	%			
Gel Content ¹					
> 200.0 µm	300	pcs/m ²			
0.700 to 1.50 mm	3.00	pcs/m ²			
1.50 to 2.50 mm	0.00	pcs/m ²			
> 2.50 mm	0.00	pcs/m²			
Thermal Creep Temperature ²	90 to 96	°C			
Thermal-oxidative Deterioration (150°C)	15.0	day			
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	82 to 95				
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	32.0	MPa	ASTM D638		
Tensile Elongation (Yield)	10	%	ASTM D638		
Flexural Modulus	1250	MPa	ASTM D790		
Thermal	Nominal Value	Unit			

Vicat Softening Temperature ³	150 to 154	°C	
NOTE			
1.	p.4.8 ?U 2211-136-0576	5801-2006	
2.	at load 0.46 H/mm ²		
3.	in liquid medium under	force 10 H	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

