

STABAMID® 25 AE 1

Polyamide 66
Solvay Polyamide & Intermediates

Message:

STABAMID® 25 AE 1 is a Polyamide 66 (Nylon 66) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.
Typical application of STABAMID® 25 AE 1: Additive/Masterbatch

General Information		
Features	General Purpose	
Uses	General Purpose	
	Plastics Modification	
Forms	Pellets	
Physical	Nominal Value	Unit
Density	1.14	g/cm³
Apparent Density	0.70	g/cm³
Humidity - at Packaging	< 0.35	%
Relative Viscosity		
Formic Acid 90%	42.9	
Sulfuric Acid 96%	2.55	
Viscosity		
Formic Acid 90%	126	cm³/g
Sulfuric Acid 96%	138	cm³/g
Black Spot		
> 300.0 µm	< 5.00	n°/kg
< 1.00 mm	< 5.00	n°/kg
> 1.00 mm	0.00	n°/kg
Granulometry ¹	2.50 to 3.00	
Thermal	Nominal Value	Unit
Melting Temperature ²	260	°C
Peak Crystallization Temperature (DSC)	220	°C
Optical	Nominal Value	Unit
Yellowness Index	< 1.0	YI
NOTE		
1.	g/100 chips	
2.	2nd melting	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

