

SCHULADUR® A GF 10

Polybutylene Terephthalate

A. Schulman Europe

Message:

10% glass fibre reinforced PBT-grade

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PBT-GF		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	30.0	cm ³ /10min	ISO 1133
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4500	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	90.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.5	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	215	°C	ISO 75-2/Bf
1.8 MPa, not annealed	185	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms · cm	IEC 60093
Comparative Tracking Index	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
1.50 mm	HB		IEC 60695-11-10, -20
3.00 mm	HB		IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	650	°C	IEC 60695-2-12
3.00 mm	650	°C	IEC 60695-2-12
Additional Information			

1.)
Not for use in food contact applications2.)
Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

