

Celanex® 5200-2

Polybutylene Terephthalate

Celanese Corporation

Message:

Celanex 5200-2 is a 15% fiberglass reinforced polyester with improved surface finish. Celanex 5200-2 contains an internal lubricant.

General Information			
UL YellowCard	E45575-239400		
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Additive	Lubricant		
Features	Lubrication		
	General		
	Excellent appearance		
Uses	General		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)	28	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (265°C/2.16 kg)	38.0	cm ³ /10min	ISO 1133
Molding Shrinkage			
Flow	0.40 - 0.60	%	ASTM D955
Flow direction	0.40 - 0.60	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	91		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ISO 527-2/1A/1
Tensile Strength			
Fracture, 23°C	89.6	MPa	ASTM D638
Fracture	120	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	2.0	%	ASTM D638
Fracture	3.0	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	8000	MPa	ISO 178
Flexural Stress (23°C)	185	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA

23°C	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	35	kJ/m ²	ISO 179/1eU
23°C	35	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	7.1	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	215	°C	ISO 75-2/B
0.45 MPa, annealed	216	°C	ASTM D648
1.8 MPa, not annealed	179	°C	ASTM D648
1.8 MPa, not annealed	190	°C	ISO 75-2/A
8.0 MPa, not annealed	65.0	°C	ISO 75-2/C
Vicat Softening Temperature	210	°C	ISO 306/B50
Melting Temperature ¹	225	°C	ISO 11357-3, ASTM D3418
CLTE - Flow	3.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity			
--	1.0E+16	ohms · cm	ASTM D257
--	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength			
-- ²	19	kV/mm	ASTM D149
--	28	kV/mm	IEC 60243-1
Dielectric Constant			
1 MHz	3.70		ASTM D150
100 Hz	4.30		IEC 60250
1 MHz	4.00		IEC 60250
Dissipation Factor			
1 MHz	2.0E-3		ASTM D150
100 Hz	1.1E-3		IEC 60250
1 MHz	0.019		IEC 60250
Comparative Tracking Index	325	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	HB		UL 94
Oxygen Index	20	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	20.0 - 50.0	°C	
Rear Temperature	230 - 250	°C	
Middle Temperature	235 - 255	°C	

Front Temperature	235 - 255	°C
Nozzle Temperature	250 - 265	°C
Processing (Melt) Temp	235 - 265	°C
Mold Temperature	65.0 - 93.0	°C
Injection Rate	Moderate-Fast	

Injection instructions

Manifold Temperature: 250 to 265°CZone 4 Temperature: 240 to 260°CFeed Temperature: 230 to 250°C

NOTE

- | | |
|----|-----------------------|
| 1. | 10°C/min |
| 2. | Method A (short time) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

