

POCAN® T 7323 000000

Polybutylene Terephthalate + PET

LANXESS GmbH

Message:

PBT+PET, 20 % glass fibers, injection molding, improved surface finish, increased temperature peak load

General Information	
UL YellowCard	E245249-474061
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight
Features	Excellent appearance
Agency Ratings	EC 1907/2006 (REACH)
Processing Method	Injection molding
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)
	Isochronous Stress vs. Strain (ISO 11403-1)
	Isothermal Stress vs. Strain (ISO 11403-1)
	Secant Modulus vs. Strain (ISO 11403-1)
	Shear Modulus vs. Temperature (ISO 11403-1)
	Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.47	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 270°C, 2.00mm ¹	1.0	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.20	%	ISO 294-4
Flow direction: 270°C, 2.00mm ³	0.40	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.10	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	0.40	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Viscosity Number (Reduced Viscosity)	92.0	ml/g	ISO 1628
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	175	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	7500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	120	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.2	%	ISO 527-2/5
Tensile Creep Modulus			ISO 899-1

1 hr	7200	MPa	ISO 899-1
1000 hr	6100	MPa	ISO 899-1
Flexural Modulus ⁵ (23°C)	7500	MPa	ISO 178/A
Flexural Stress ⁶			
3.5% strain	195	MPa	ISO 178/A
23°C	195	MPa	ISO 178
Flexural Strain at Flexural Strength (23°C) ⁷	3.5	%	
Halving Interval			IEC 60216
-- ⁸	10.2	°C	IEC 60216
1.50 mm ⁹	13.5	°C	IEC 60216
1.50 mm ¹⁰	10.2	°C	IEC 60216
Temperature index ¹¹			IEC 60216
Electric Strength	150		IEC 60216
Tensile Impact Strength : 1.50 mm	130		IEC 60216
Tensile Strength : 1.50 mm	150		IEC 60216
Electrolytical Corrosion	A 1		IEC 60426
ISO Shortname	PBT+PET, GHMR, 09-070, GF20		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	35	kJ/m ²	ISO 179/1eU
23°C	40	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-40°C	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	35	kJ/m ²	ISO 180/1U
23°C	35	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	195	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B50
Ball Pressure Test (215°C)	Pass		IEC 60695-10-2
Melting Temperature ¹²	225 - 250	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	3.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2

Thermal Conductivity (23°C)	0.26	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity (23°C)	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	24	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.80		IEC 60250
23°C, 1 MHz	3.60		IEC 60250
Dissipation Factor			IEC 60250
23°C, 100 Hz	1.8E-3		IEC 60250
23°C, 1 MHz	0.017		IEC 60250
Comparative Tracking Index (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		UL 94
1.60 mm	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Oxygen Index ¹³	21	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	260 - 280	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2; MT 90°C; 600 Bar		
2.	60x60x2		
3.	60x60x2; MT 90°C; 600 Bar		
4.	60x60x2		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	Electric Strength		
9.	Tensile Impact Strength		
10.	Tensile Strength		
11.	20000 h		
12.	10°C/min		
13.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

