

Karina IVORY PVC COMPOUND

TR-601D35/1-Y-IS

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

PVC COMPOUND FOR EXTRUSION OF AUTOMOTIVE PROFILES.

General Information			
Uses	Automotive Applications Profiles		
Appearance	Ivory		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.17 to 1.23	g/cm ³	IEC 60811-1-3
Cadmium Content	< 50	ppm	IEC 62321
Chromium Content	< 100	ppm	IEC 62321
Color	OK		ME 12
Color a	-2.14 to 0.860		ME 12
Color b	2.01 to 5.01		ME 12
Color L	83.5 to 86.5		ME 12
Mercury Content	< 100	ppm	IEC 62321
Bromine Content	< 100	ppm	IEC 62321
Lead Content	< 100	ppm	IEC 62321
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	58 to 62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	> 9.81	MPa	IEC 60811-1-1
Tensile Strain (Yield)	> 320	%	IEC 60811-1-1
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

