

DOMAMID® 6G20V0EF

Polyamide 6

DOMO Engineering Plastics SPA

Message:

Polyamide 6, 20% glass fibre reinforced, flame retardant, halogen and red phosphorous free, for injection moulding.

General Information			
UL YellowCard	E170540-532327		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	Low (to None) Phosphorus Content		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2/1
Tensile Stress (Break)	115	MPa	ISO 527-2/5
Tensile Strain (Break)	2.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	6.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	218 to 222	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	V-0		UL 94
Glow Wire Flammability Index (1.00 to 3.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

