

XENOY™ X5230 resin

Polycarbonate + PET

SABIC Innovative Plastics Europe

Message:

Mineral filled PC/PET blend with high flow, high heat, dimensional stability, low shrinkage and low CTE, especially for painted applications

General Information			
Filler / Reinforcement	Mineral filler		
Features	Good dimensional stability		
	High liquidity		
	Heat resistance, high		
	Low shrinkage		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (265°C/5.0 kg)	28	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (265°C/5.0 kg)	24.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow ¹	0.50 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.42	%	ISO 62
Equilibrium, 23°C, 50% RH	0.14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3990	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield	53.0	MPa	ISO 527-2/5
Fracture	34.0	MPa	ISO 527-2/5
Tensile Strain			ISO 527-2/5
Yield	3.4	%	ISO 527-2/5
Fracture	21	%	ISO 527-2/5
Flexural Modulus ²	3820	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	14	kJ/m ²	ISO 179/1eA
Notched Izod Impact ⁴			ISO 180/1A
-30°C	6.0	kJ/m ²	ISO 180/1A
23°C	8.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁵			ISO 180/1U
-30°C	120	kJ/m ²	ISO 180/1U

23°C	140	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁶ (1.8 MPa, Unannealed, 64.0 mm Span)	100	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	137	°C	ISO 306/B50
--	140	°C	ISO 306/B120
Linear thermal expansion coefficient			ISO 11359-2
Flow: -30 to 80°C	4.5E-5	cm/cm/°C	ISO 11359-2
Horizontal: -30 to 80°C	9.7E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	110 - 120	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 - 80.0	°C	
Rear Temperature	240 - 270	°C	
Middle Temperature	250 - 275	°C	
Front Temperature	260 - 280	°C	
Nozzle Temperature	260 - 275	°C	
Processing (Melt) Temp	265 - 275	°C	
Mold Temperature	60.0 - 100	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4 sp=62mm		
4.	80*10*4		
5.	80*10*4		
6.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT