

COSMOPLENE® AH561

Polypropylene Copolymer

TPC, The Polyolefin Company (Singapore) Pte Ltd

Message:

COSMOPLENE AH561 is high impact PP copolymer manufactured by gas phase process licensed from Sumitomo Chemical Co. Japan.
COSMOPLENE AH561 is low flow, super impact copolymer grade.

General Information			
Features	High Impact Resistance		
	Impact Copolymer		
	Low Flow		
Uses	Appliance Components		
	Containers		
	Crates		
	Electrical/Electronic Applications		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a		
UL File Number	E108370		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	3.0	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Flow : 2.00 mm	1.6	%	
Across Flow : 2.00 mm	1.6	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	26.0	MPa	
Break	22.0	MPa	
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	59	J/m	
23°C	140	J/m	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	112	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	190 to 230	°C	
Middle Temperature	190 to 230	°C	
Front Temperature	190 to 230	°C	
Mold Temperature	30.0	°C	
Injection Pressure	6.86	MPa	
Clamp Tonnage	0.98	kN/cm ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

