

Pyramid™ II230

Polyether Imide

Polymics, Ltd.

Message:

Compression Molded Shape, Polyetherimide, Electro-Static Dissipative

General Information			
Features	Rapid Static Decay		
	Statically Conductive		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	1.4	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4100	MPa	ASTM D638
Tensile Strength	75.9	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	3400	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.318 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	°C	ASTM D648
CLTE - Flow	5.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			ESD S11.11
-- ¹	1.0E+8 to 1.0E+11	ohms	
-- ²	1.0E+9 to 1.0E+12	ohms	
Volume Resistivity			ESD S11.12
-- ³	1.0E+8 to 1.0E+11	ohms · cm	
-- ⁴	1.0E+9 to 1.0E+12	ohms · cm	
Static Decay	0.00200		FTMS 101C 4046.1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
NOTE			
1.	100 Volts		

2.	10 Volts
3.	100 Volts
4.	10 Volts

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

