

Sarlink® TPE ME-2170N

Thermoplastic Elastomer

Teknor Apex Company

Message:

Sarlink®TPE ME-2170N is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.
Sarlink®The typical application field of TPE ME-2170N is: automobile industry

General Information			
Uses	Automotive exterior parts		
Appearance	Opacity		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/2.16 kg)	11	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	6.50	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	199 - 210	°C	
Middle Temperature	204 - 216	°C	
Front Temperature	210 - 221	°C	
Nozzle Temperature	216 - 227	°C	
Processing (Melt) Temp	216 - 227	°C	
Mold Temperature	35.0 - 65.6	°C	
Injection Pressure	1.38 - 6.89	MPa	
Injection Rate	Fast		
Back Pressure	0.172 - 0.862	MPa	
Screw Speed	50 - 120	rpm	
Cushion	3.81 - 25.4	mm	
Injection instructions			
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	193 - 204	°C	
Cylinder Zone 2 Temp.	199 - 210	°C	
Cylinder Zone 3 Temp.	204 - 216	°C	
Cylinder Zone 5 Temp.	210 - 221	°C	

Die Temperature	216 - 227	°C
-----------------	-----------	----

Extrusion instructions

Screw Speed: 30 to 100 rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT