

CALP 3511G

Polyolefin

Lion Idemitsu Composites Co., Ltd.

Message:

CALP 3511G is a Polyolefin product. It can be processed by injection molding and is available in Asia Pacific.

Characteristics include:

Flame Rated

Food Contact Acceptable

High Gloss

General Information			
UL YellowCard	E220017-266434		
Features	Food Contact Acceptable		
	High Gloss		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	12	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Flow : 2.00 mm	1.5	%	
Across Flow : 2.00 mm	1.1	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	35.0	MPa	ASTM D638
Tensile Elongation (Break)	17	%	ASTM D638
Flexural Modulus	2780	MPa	ASTM D790
Flexural Strength	54.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	5.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	134	°C	ASTM D648
Ball Pressure Test (150°C)	Pass		Internal Method
RTI Elec	105	°C	UL 746
RTI Imp	105	°C	UL 746
RTI Str	105	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	HB	UL 94	
Optical	Nominal Value	Test Method	
Gloss	80	ASTM D2457	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

