

CEFOR™ 1050P

Linear Low Density Polyethylene Resin

The Dow Chemical Company

Message:

CEFOR 1050P is a Linear Low Density Polyethylene Resin 1-Butene copolymer, produced in the Solution process. This resin is designed to be used in cast extrusion to produce films for stretch and health & hygiene applications.

Complies with:

European Commission Regulation (EU) No 10/2011

U.S. FDA 21 CFR 177.1520(c)3.2a

Consult the regulation for complete details

Additive:

Antiblock: No

Slip: No

Processing Aid: No

General Information			
Agency Ratings	FDA 21 CFR 177.1520(c) 3.2a		
	Europe No 10/2011		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.916	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	24	µm	
Film Puncture Resistance (24 µm)	11.1	J/cm ³	Internal method
secant modulus			ASTM D882
2% secant, MD: 24 µm	194	MPa	ASTM D882
2% secant, TD: 24 µm	174	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 24 µm	33.6	MPa	ASTM D882
TD: Yield, 24 µm	18.1	MPa	ASTM D882
MD: Break, 24 µm	6.00	MPa	ASTM D882
TD: Break, 24 µm	5.20	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Break, 24 µm	560	%	ASTM D882
TD: Break, 24 µm	870	%	ASTM D882
Dart Drop Impact (24 µm)	50	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 24 µm	52	g	ASTM D1922
TD : 24 µm	260	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method

Gloss (45°, 23.9 μm)	93		ASTM D2457
Haze (23.9 μm)	0.94	%	ASTM D1003

Extrusion instructions

Processing Conditions for cast film analyzed:

Die gap: 31.5 mil (0.8 mm)

Melt Temperature: 455°F (235°C)

Chill Roll Temperature: 64.4°F (18°C)

Haul Off Speed: 15 m/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

