

Keplex® 3730GM5

Polybutylene Terephthalate + PET

Korea Engineering Plastics Co., Ltd

Message:

KEPEX 3730GM5 is a glass fiber and mineral 30%-reinforced/filled PBT/PET grade.

It has superior mechanical, thermal, and electrical properties. It also has high gloss and low warpage.

It is suitable for automotive, electrical & electronics, and industrial parts requiring high stiffness and heat resistance.

The listed values are for the natural grade.

General Information			
Filler / Reinforcement	Glass \mineral, 30% filler by weight		
Features	Low warpage		
	Rigidity, high		
	Highlight		
	Good electrical performance		
	Heat resistance, high		
Uses	Electrical/Electronic Applications		
	Industrial components		
	Application in Automobile Field		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
shrinkage-Flow (3.00 mm)	0.40 - 0.80	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	125	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	9400	MPa	ISO 178
Flexural Stress	185	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.2	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	210	°C	ISO 75-2/A
Melting Temperature ¹	220 - 250	°C	ISO 11357-3

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Dielectric Strength	22	kV/mm	IEC 60243-1
Dielectric Constant (60 Hz)	3.40		ASTM D150
Dissipation Factor (60 Hz)	2.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	3.0 - 5.0	hr	
Suggested Max Moisture	0.050	%	
Hopper Temperature	60 - 80	°C	
Rear Temperature	245	°C	
Middle Temperature	255	°C	
Front Temperature	265	°C	
Nozzle Temperature	270	°C	
Mold Temperature	70 - 90	°C	
Back Pressure	0.490 - 0.981	MPa	
Screw Speed	80 - 120	rpm	
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT