

Bergamid™ A700 TM-YF

Polyamide 66
PolyOne Corporation

Message:

Bergamid™ A700 TM-YF is a Polyamide 66 (Nylon 66) product. It can be processed by extrusion or injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information				
RoHS Compliance		RoHS Compliant		
UL File Number		E76261		
Forms		Pellets		
Processing Method		Extrusion		
		Injection Molding		

Physical	Dry	Conditioned	Unit	Test Method
Density ¹	1.08	--	g/cm ³	DIN 53479
Water Absorption				ISO 62
Saturation, 23°C	6.7	--	%	
Equilibrium, 23°C, 50% RH	2.2	--	%	

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus ² (23°C)	2000	1200	MPa	ISO 527-2/1
Tensile Stress ³ (Yield, 23°C)	50.0	40.0	MPa	ISO 527-2/50
Tensile Strain ⁴ (Yield, 23°C)	6.0	40	%	ISO 527-2/50

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.0	--	kJ/m ²	
23°C	25	--	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	--		
23°C	No Break	No Break		

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	200	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	--	°C	ISO 75-2/A

Maximum Use Temperature				IEC 60216
-- ⁵	80	--	°C	
Short Time	180	--	°C	
Melting Temperature (DSC)	261	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength	90	55	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.30	3.60		IEC 60250
Dissipation Factor (1 MHz)	0.016	0.060		IEC 60250
Comparative Tracking Index (Solution A)	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time - Desiccant Dryer	4.0 to 8.0		hr	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	40.0 to 80.0		°C	
Back Pressure	50.0 to 150		MPa	
NOTE				
1.	±0.02 g/cm ³			
2.	dry as moulded			
3.	dry as moulded			
4.	dry as moulded			
5.	Continuous (GTP 50% Tensile)			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT