

PELPRENE™ P40H-05

Thermoplastic Polyester Elastomer

TOYOBO America, Inc.

Message:

PELPRENE™ P40H-05 is a Thermoplastic Polyester Elastomer (TPEE) product. It is available in North America.

Characteristics include:

Flame Rated

Low to No Odor/Taste

General Information			
UL YellowCard	E51743-242522		
Features	Low to No Odor		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	0.50	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 65% RH)	0.48	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			
Shore A	89		JIS K6301
Shore D	38		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	23.0	MPa	
50% Strain	6.40	MPa	
Tensile Elongation (Break)	690	%	ASTM D638
Flexural Modulus	51.0	MPa	ASTM D790
Compressive Strength (10% Strain)	4.50	MPa	ASTM D695
Taber Abrasion Resistance (1000 Cycles)	20.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	98.0	kN/m	ASTM D624
Compression Set	50	%	JIS K6301
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	< 25.0	°C	ASTM D648
Brittleness Temperature	< -65.0	°C	JIS K6301
Vicat Softening Temperature	120	°C	ASTM D1525
Melting Temperature	172	°C	DSC

CLTE - Flow	1.7E-4	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+12	ohms·cm	ASTM D257
Dielectric Strength	20	kV/mm	JIS K2111
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Resilience	78	%	JIS K6301

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

