

VYLOPET® EMC317A

Polycarbonate + PBT

TOYOBO America, Inc.

Message:

VYLOPET® EMC317A is a polycarbonate polybutene terephthalate (PC PBT) product. It is available in North America.

Features include:

flame retardant/rated flame

Rapid Prototyping Cycle

General Information			
UL YellowCard	E51743-242569		
Features	Fast molding cycle		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.90	g/cm ³	ASTM D792
	0.90		
Molding Shrinkage - Flow (3.00 mm)	0.50	%	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	75.0	MPa	ASTM D638
Tensile Elongation (Break)	1.6	%	ASTM D638
Flexural Modulus	8900	MPa	ASTM D790
Flexural Strength (Yield)	120	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, CS-17 Wheel)	40.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	38	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	240	°C	ASTM D648
1.8 MPa, not annealed	205	°C	ASTM D648
Melting Temperature	255	°C	DSC
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	1.0E+18	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	25	kV/mm	ASTM D149
Arc Resistance	125	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
Ball Pressure Temperature, UL746, Method B: 225 °CComparative Tracking Index, IEC Pub1.112: Class 2			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	255 - 265	°C	
Mold Temperature	90.0 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT