

LUVOCOM® 1106-7223

Polyether Imide
Lehmann & Voss & Co.

Message:

LUVOCOM® 1106-7223 is a polyetherimide (PEI) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 1106-7223 are:

Flame Retardant

Good dimensional stability

Heat resistance

Lubrication

General Information			
Additive	PTFE lubricant		
Features	Good dimensional stability		
	Heat resistance, high		
	Lubrication		
	Flame retardancy		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Molding Shrinkage	0.50 - 0.70	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2
Tensile Stress (Break)	95.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress	140	MPa	ISO 178
Flexural Strain at Flexural Strength	7.8	%	ISO 178
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	170	°C	UL 746B
Injection	Nominal Value	Unit	
Drying Temperature			
Hot air dryer, A	120	°C	
Hot air dryer, B	150	°C	
Drying Time			

Hot air dryer, A	> 8.0	hr
Hot air dryer, B	> 4.0	hr
Suggested Max Moisture	0.030	%
Rear Temperature	330 - 350	°C
Middle Temperature	340 - 390	°C
Front Temperature	350 - 400	°C
Nozzle Temperature	350 - 400	°C
Processing (Melt) Temp	380	°C
Mold Temperature	150 - 180	°C
Injection instructions		

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.03%, otherwise porosity and surface defects (e.g. smearing) may occur. Predrying is recommended even when sealed original containers are being used. To avoid internal stresses, a low shear load should be used for processing.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

High-temperature polymers place increased demands on the tool steels employed.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

