

Bynel® 2002

Ethylene Acrylic Acid Copolymer

DuPont Packaging & Industrial Polymers

Message:

BYNEL® Series 2000 resins are acid modified ethylene acrylate resins. They contain a temperature stable ester which makes them functional in high temperature coextrusions. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

Applications

BYNEL 2000 series resins adhere to a wide variety of materials. They are most often used to adhere to PE, EVA, Polyamide, ionomer, paper, aluminum foil, and printed films.

BYNEL 2002 is designed for low melt temperature extrusion or coextrusion coating / laminating applications.

General Information			
Agency Ratings	FDA 21 CFR 177.1330		
Forms	Particle		
Processing Method	Co-extrusion molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ASTM D1238, ISO 1133
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	60.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	91.0	°C	ASTM D3418, ISO 3146
Freezing Point	66	°C	ASTM D3418
Additional Information			
The value listed as Melting Point, DSC, was tested in accordance with ASTM D3418. Freezing Point (DSC), ASTM D3418: 66°C			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	135	°C	
Cylinder Zone 2 Temp.	185	°C	
Cylinder Zone 3 Temp.	235	°C	
Cylinder Zone 4 Temp.	260	°C	
Cylinder Zone 5 Temp.	260	°C	
Adapter Temperature	260	°C	
Melt Temperature	< 285	°C	
Die Temperature	260	°C	
Extrusion instructions			

Processing conditions shown are for extrusion coating/lamination.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT