

Wondel® A AN0F

Polyamide 66

Nanjing Julong Engineering Plastics Co., LTD

Message:

Wondel® A AN0F is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific.

Important attributes of Wondel® A AN0F are:

- Flame Rated
- Good Mold Release
- High Flow

General Information			
Features	Good Mold Release		
	High Flow		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm³	ISO 1183
Molding Shrinkage	1.3 to 1.8	%	ISO 294-4
Water Absorption (23°C, 24 hr)	8.5	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	80.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Stress	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	4.0	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	200	°C	ISO 75-2/B
Melting Temperature (DSC)	251	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

