

Adsyl 7622 XCP

Polyolefin

LyondellBasell Industries

Message:

Adsyl 7622 XCP is an advanced polyolefin, specially designed for use as a sealing or metallized layer in co-extruded film applications.

This grade features a very low seal initiation temperature and good optics.

It does not contain slip or anti-block additives.

For regulatory information please refer to Adsyl 7622 XCP Product Stewardship Bulletin (PSB).

General Information			
Features	Low temperature heat sealability Electroplating Optical		
Uses	Bi-axially Oriented Film Films Laminate cast film Food packaging Shrinkable film		
Processing Method	Film extrusion Co-extrusion molding cast film		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.5	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus			ISO 527-3/25
MD: 50 µm, cast film	280	MPa	ISO 527-3/25
TD: 50 µm, cast film	280	MPa	ISO 527-3/25
Tensile Stress			ISO 527-3/500
MD: yield, 50 µm, cast film	14.0	MPa	ISO 527-3/500
TD: yield, 50 µm, cast film	14.0	MPa	ISO 527-3/500
MD: fracture, 50 µm, casting film	45.0	MPa	ISO 527-3/500
TD: fracture, 50 µm, casting film	35.0	MPa	ISO 527-3/500
Tensile Elongation			ISO 527-3/500
MD: yield, 50 µm, cast film	17	%	ISO 527-3/500

TD: yield, 50 μm, cast film	15	%	ISO 527-3/500
MD: fracture, 50 μm, casting film	900	%	ISO 527-3/500
TD: fracture, 50 μm, casting film	800	%	ISO 527-3/500
Seal Initiation Temperature	105	°C	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	62.0	°C	ISO 75-2/B
Vicat Softening Temperature	107	°C	ISO 306/A50
Melting Temperature	132	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 50.0 μm)	88		ASTM D2457
Haze (50.0 μm)	0.60	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

