

ColorRx® TPE-OM60A0RXTL

Thermoplastic Elastomer

LTL Color Compounders, Inc.

Message:

A biocompatible, translucent, 60 Shore A Thermoplastic Elastomer with good sterilizability (including radiation) for healthcare applications. For over-molding and other applications.

General Information			
Features	Biocompatible		
	Good Sterilizability		
	Radiation Sterilizable		
Uses	Medical/Healthcare Applications		
	Overmolding		
Agency Ratings	ISO 10993		
	USP Class VI		
Appearance	Translucent		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9.17	MPa	ASTM D412
Tensile Elongation (Break)	830	%	ASTM D412
Compression Set			ASTM D395B
23°C, 22 hr	20	%	
70°C, 22 hr	33	%	
100°C, 22 hr	49	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT