

Multilon® T-3615Q

Polycarbonate + ABS

TEIJIN LIMITED

Message:

PC/ABS polymer alloy

General Information			
UL YellowCard	E98529-253614	E244324-101599293	
Features	Permanent Antistatic		
Uses	Electrical Parts		
	General Purpose		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.50 to 0.70	%	
Flow : 4.00 mm	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1760	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	45.0	MPa	
Break	50.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	3.0	%	
Break	120	%	
Flexural Modulus ¹	1800	MPa	ISO 178
Flexural Stress ²	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	80	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	107	°C	ISO 75-2/B
1.8 MPa, Unannealed	93.0	°C	ISO 75-2/A
Vicat Softening Temperature	109	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow	8.0E-5	cm/cm/°C	
Transverse	8.0E-5	cm/cm/°C	

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10 to 1.0E+11	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT