

Makrolon® Sheet UV

Polycarbonate
Covestro - Polycarbonates

Message:

Makrolon® UV sheet is a transparent polycarbonate product with an advanced UV resistance technology that assures long lasting outdoor weathering performance in flat and curved glazing applications. It has higher impact resistance than acrylic and glass, and it can be cold-formed during installation. Makrolon UV is produced with high optical quality and minimal distortion in clear, a range of standard architectural tints, or can be custom matched to any color. Makrolon UV has a ten (10) year Limited Product Warranty against breakage, yellowing, and loss of light transmission. The terms of the warranty are available upon request.

Applications
Awnings, entryway canopies, skylights, barrel vaults, glazed archways, covered pedestrian walkways, and sloped, vertical, and curved glazing

General Information			
UL YellowCard	E351891-101049033	E351891-101049034	
Additive	UV stabilizer		
Features	UV Stabilized		
	Impact resistance, good		
	Good weather resistance		
	Definition, high		
Uses	Assembled glass		
Agency Ratings	ANSI Z 97.1		
	CPSC 16 CFR 1201 Category I		
	CPSC 16 CFR 1201 Category II		
	ICC-ES Evaluation Report ESR-2728		
	UL 972		
Appearance	Available colors		
	Clear/transparent		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	70		ASTM D785
Class r	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2340	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	62.1	MPa	ASTM D638

Limit	65.5	MPa	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Flexural Modulus	2380	MPa	ASTM D790
Flexural Strength	93.1	MPa	ASTM D790
Compressive Modulus	2380	MPa	ASTM D695
Compressive Strength	86.2	MPa	ASTM D695
Shear Modulus	786	MPa	ASTM D732
Shear Strength			ASTM D732
-- ¹	68.9	MPa	ASTM D732
-- ²	41.4	MPa	ASTM D732
Poisson's Ratio	0.38		ASTM E132
Wear resistance-Delta Haze ³	2	%	ASTM D1044
Shading Coefficient			NFRC 100-2010
Clear : 5.99 mm	0.970		NFRC 100-2010
Gray or Bronze : 5.99 mm	0.770		NFRC 100-2010
U Factor			NFRC 100-2010
Summer : 5.99 mm	0.850	BTU/hr/ft ² /°F	NFRC 100-2010
Summer : 9.53 mm	0.780	BTU/hr/ft ² /°F	NFRC 100-2010
Winter : 5.99 mm	0.920	BTU/hr/ft ² /°F	NFRC 100-2010
Winter : 9.53 mm	0.850	BTU/hr/ft ² /°F	NFRC 100-2010
Flash Ignition Temperature	440	°C	ASTM D1929
Horizontal Burn - AEB		cm	ASTM D635
Self Ignition Temperature	550	°C	ASTM D1929
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	850	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	No Break		ASTM D256
Instrumented Dart Impact (3.18 mm)	> 63.7	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	138	°C	ASTM D648
1.8 MPa, not annealed	132	°C	ASTM D648
Brittleness Temperature	-129	°C	ASTM D746
CLTE - Flow	6.8E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.19	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	8.2E+16	ohms · cm	ASTM D257
Dielectric Strength (3.18 mm, in Air)	15	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
10 Hz	2.96		ASTM D150
60 Hz	3.17		ASTM D150
Dissipation Factor (60 Hz)	9.0E-4		ASTM D150
Arc Resistance			ASTM D495

-- ⁴	10.0	sec	ASTM D495
-- ⁵	120	sec	ASTM D495
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance			ASTM D1003
3000 μm ⁶	86.0	%	ASTM D1003
3000 μm ⁷	50.0	%	ASTM D1003
3000 μm ⁸	50.0	%	ASTM D1003
3000 μm ⁹	18.0	%	ASTM D1003

NOTE

- | | |
|----|--------------------------------------|
| 1. | Ultimate |
| 2. | Yield |
| 3. | 100 Cycles, CS-10F Wheel, 500 g load |
| 4. | Steel Strip Electrode |
| 5. | Tungsten Electrodes |
| 6. | Clear |
| 7. | I30 Gray |
| 8. | K09 Bronze |
| 9. | I35 Dark Gray |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT