

POCAN® KU 2-7241 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 25 % glass fibers, injection molding, flame retardant, improved impact strength

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 25% filler by weight		
Additive	Flame retardancy		
Features	Impact resistance, good		
	Flame retardancy		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PBT GF FR (17)		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.58	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	28.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	1.0	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.20	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	0.30	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.10	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	8700	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	115	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.3	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	7800	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% strain, 23°C	190	MPa	ISO 178/A
23°C ⁶	195	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.6	%	ISO 178/A
ISO Shortname	PBT, GFHMPR, 11-090, GF25		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	12	kJ/m ²	ISO 179/1eA

Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	55	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	190	°C	ISO 75-2/A
8.0 MPa, not annealed	110	°C	ISO 75-2/C
Vicat Softening Temperature	200	°C	ISO 306/B50
Ball Pressure Test (207°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	3.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	> 1.0E+16	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	30	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.80		IEC 60250
23°C, 1 MHz	3.70		IEC 60250
Comparative Tracking Index (CTI)	PLC 3		UL 746
Comparative Tracking Index (Solution A)	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		UL 94
1.50 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.750 mm	960	°C	IEC 60695-2-12
1.50 mm	960	°C	IEC 60695-2-12
3.00 mm	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	750	°C	IEC 60695-2-13
1.50 mm	725	°C	IEC 60695-2-13
3.00 mm	725	°C	IEC 60695-2-13
Oxygen Index ⁹	32	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	

Processing (Melt) Temp	250 - 270	°C
Mold Temperature	80.0 - 100	°C

NOTE		
1.	60x60x2mm, 80°C MT, 600 bar	
2.	60x60x2mm	
3.	60x60x2mm, 80°C MT, 600 bar	
4.	60x60x2mm	
5.	2.0 mm/min	
6.	2.0 mm/min	
7.	2 mm/min	
8.	10°C/min	
9.	Procedure A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT