

Hylex® P1017 L2 HB

Polycarbonate

Entec Polymers

Message:

Hylex® P1017 L2 HB is a Polycarbonate (PC) material. It is available in North America.

Important attributes of Hylex® P1017 L2 HB are:

- Flame Rated
- RoHS Compliant
- Good Mold Release
- High Flow
- Mold Release Agent

General Information			
UL YellowCard	E157012-538664		
Additive	Mold Release		
Features	Good Mold Release		
	High Flow		
RoHS Compliance	RoHS Compliant		
Appearance	Blue		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	17	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 23°C)	68.9	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	130	%	ASTM D638
Flexural Modulus (23°C)	2340	MPa	ASTM D790
Flexural Strength (23°C)	95.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	138	°C	
1.8 MPa, Unannealed	129	°C	
Vicat Softening Temperature	154	°C	ASTM D1525
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257

Dielectric Strength (23°C, 3.18 mm, In Air)	15	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance (3180 μm)	88.0	%	ASTM D1003
Haze (3180 μm)	1.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

