

LUBAN™ 1104 KTI

Polypropylene Homopolymer

Oman Oil Refineries & Petroleum Industries Co. (Orpic)

Message:

Luban polypropylene is manufactured using Novolen vertical stirred Gas-phase polymerization process.

1104 KTI is a homopolymer polypropylene with narrow MFR-range.

Applications - Metallizable BOPP, Raffia

General Information			
Additive	Anti-gas fading		
Features	Homopolymer		
	Metallizable		
Uses	Bi-axially Oriented Film		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.2	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1450	MPa	ISO 527-2/1
Tensile Stress (Yield)	34.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	9.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	190	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	85.0	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT