

# Hyprom-G™ PP-CP70

Polypropylene Impact Copolymer

Entec Polymers

## Message:

Impact Copolymer, 70 Melt Flow

This product meets the requirements of the US Food and Drug Administration as specified in 21 CFR 177.1520.

General Information			
Features	Impact copolymer		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	70	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	26.0	MPa	ASTM D638
Tensile Elongation (Break)	< 100	%	ASTM D638
Flexural Modulus	1600	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	120	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT