

Ultrason® E 2010 HC

Polyethersulfone

BASF Corporation

Message:

Special unreinforced, medium viscosity injection moulding grade for applications demanding inherent color, transparency and free from specks.

General Information			
Features	Medium Viscosity		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Resin ID (ISO 1043)	PESU		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Apparent Density	0.70 to 0.80	g/cm ³	
Melt Volume-Flow Rate (MVR) (360°C/10.0 kg)	70.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.86	%	
Flow	0.82	%	
Water Absorption			ISO 62
Saturation, 23°C	2.2	%	
Equilibrium, 23°C, 50% RH	0.80	%	
Viscosity Number ¹	56.0	cm ³ /g	ISO 307
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	154	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2650	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	6.9	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.5	kJ/m ²	
23°C	7.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		

23°C	No Break		
Notched Izod Impact Strength			ISO 180/A
-30°C	7.5	kJ/m ²	
23°C	7.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	205	°C	ISO 75-2/A
Glass Transition Temperature ²	225	°C	ISO 11357-2
CLTE - Flow			
23 to 80°C	5.2E-5	cm/cm/°C	ISO 11359-2
180°C	5.9E-5	cm/cm/°C	DIN 53752
Maximum Service Temperature - short cycle operation	220	°C	
Temperature Index - at 50% loss of tensile strength ³	180	°C	IEC 60216
Screw Speed	< 300	mm/sec	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.90		
1 MHz	3.80		
Dissipation Factor			IEC 60250
100 Hz	1.7E-3		
1 MHz	0.014		
Comparative Tracking Index			IEC 60112
Solution A	100	V	
Solution B	100	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.00 mm	V-0		
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.630		ISO 489
Transmittance (2000 µm)	88.0	%	DIN 5036
Injection	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	80.0	°C	
Rear Temperature	340	°C	
Middle Temperature	350	°C	
Front Temperature	360	°C	

Nozzle Temperature	360	°C
Processing (Melt) Temp	340 to 390	°C
Mold Temperature	140 to 180	°C

NOTE

1.	in 0,01 g/ml Phenol/1,2, ortho-Dichlorbenzol, 1:1
2.	10°C/min
3.	20000 h

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

