

Sarlink® TPV 24473

Thermoplastic Vulcanizate

Teknor Apex Company

Message:

Sarlink® TPV 24473 is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is extrusion or injection molding.

Typical application areas include:

engineering/industrial accessories

medical/health care

Hose

application of coating

General Information			
Uses	Plug		
	Washer		
	Washer		
	Pipe fittings		
	Shock Absorbing Pad		
	Medical/nursing supplies		
	Seals for medical pumps		
	Assembled glass		
Appearance	Opacity		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.925	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	7.03	MPa	ASTM D412
Tensile Elongation (Break)	310	%	ASTM D412
Compression Set (100°C, 22 hr)	52	%	ASTM D395B
Injection	Nominal Value	Unit	
Rear Temperature	173 - 213	°C	
Middle Temperature	179 - 219	°C	
Front Temperature	184 - 224	°C	
Nozzle Temperature	190 - 230	°C	

Processing (Melt) Temp	190 - 230	°C
Mold Temperature	35.0 - 60.0	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Fast	
Back Pressure	0.172 - 0.862	MPa
Screw Speed	50 - 120	rpm
Cushion	3.81 - 25.4	mm
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	166 - 204	°C
Cylinder Zone 2 Temp.	171 - 210	°C
Cylinder Zone 3 Temp.	177 - 216	°C
Cylinder Zone 5 Temp.	182 - 221	°C
Die Temperature	190 - 227	°C
Extrusion instructions		
螺杆转速30 - 100 rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT