

# Axiall PVC 8911

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

General purpose extrusion and molding compound. UV stabilized.

General Information	
Additive	UV stabilizer
Features	General
Forms	Particle
Processing Method	Extrusion Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	91		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	21.2	MPa	ASTM D638
100% strain	15.2	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638

Additional Information	
Recommended Stock Temperature: 375°F	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT