

RTP 700 FR

High Density Polyethylene
RTP Company

Message:
Flame Retardant

General Information			
Features	Flame Retardant		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0 to 12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.3 to 1.7	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	60		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1930	MPa	ASTM D638
Tensile Strength	16.5	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	1240	MPa	ASTM D790
Flexural Strength	24.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	27	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	270	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	104	°C	
1.8 MPa, Unannealed	93.3	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹ (in Oil)	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	2.80		ASTM D150
Dissipation Factor (1 MHz)	0.010		ASTM D150
Arc Resistance	100	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	V-0		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	79.4	°C
Drying Time	2.0	hr
Processing (Melt) Temp	193 to 232	°C
Mold Temperature	21.1 to 65.6	°C
Injection Pressure	68.9 to 103	MPa

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

