Topilene® HJ800R

Polypropylene Homopolymer

Hyosung Corporation

Message:

Characteristics:

High stiffness

Impact strength

Long term heat resistance, UL 746B

Applications:

Toaster

Coffee Maker

Steam Iron

Impact

-10°C

23°C

Unnotched Izod Impact

General Information			
Features	Good Heat Aging Resistance High Impact Resistance		
	High Stiffness		
Uses	Appliances		
	Household Goods		
	Industrial Applications		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C	C/2.16		
kg)	18	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1720	МРа	ASTM D790

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Unit

J/m

J/m

Test Method

ASTM D256

Nominal Value

39

78

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

