

ULTEM™ 2310 resin

Polyether Imide

SABIC Innovative Plastics

Message:

30% Glass fiber filled, enhanced flow Polyetherimide (Tg 217°C). ECO Conforming, UL94 V0 and 5VA listing.

General Information			
UL YellowCard	E45587-236984	E207780-100218989	E207780-100218990
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Comply with ECO		
Agency Ratings	EU Eco		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	7.6	g/10 min	ASTM D1238
Molding Shrinkage			Internal method
Flow: 3.20mm	0.20 - 0.40	%	Internal method
Transverse flow: 3.20mm	0.20 - 0.40	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	9240	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	169	MPa	ASTM D638
Fracture	159	MPa	ASTM D638
Tensile Elongation ³ (Break)	2.0	%	ASTM D638
Flexural Modulus ⁴ (100 mm Span)	9240	MPa	ASTM D790
Flexural Strength ⁵ (Break, 100 mm Span)	221	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Reverse Notch Izod Impact (3.20 mm)	440	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	210	°C	ASTM D648
Linear thermal expansion coefficient			ASTM E831
Flow: -20 to 150°C	1.6E-5	cm/cm/°C	ASTM E831
Lateral: -20 to 150°C	4.1E-5	cm/cm/°C	ASTM E831
RTI Elec	180	°C	UL 746
RTI Imp	170	°C	UL 746
RTI	180	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ⁶	PLC 6		ASTM D495

Comparative Tracking Index (CTI)	PLC 4	UL 746
High Amp Arc Ignition (HAI)	PLC 4	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3	UL 746
Hot-wire Ignition (HWI)	PLC 1	UL 746
Flammability	Nominal Value	Test Method
Flame Rating		UL 94
0.254 mm	V-0	UL 94
1.22 mm	5VA	UL 94
Injection	Nominal Value	Unit
Drying Temperature	149	°C
Drying Time	4.0 - 6.0	hr
Drying Time, Maximum	24	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 - 60	%
Rear Temperature	332 - 399	°C
Middle Temperature	338 - 399	°C
Front Temperature	343 - 399	°C
Nozzle Temperature	343 - 399	°C
Processing (Melt) Temp	349 - 399	°C
Mold Temperature	135 - 163	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm
NOTE		
1.	5.0 mm/min	
2.	Type 1, 5.0 mm/min	
3.	Type 1, 5.0 mm/min	
4.	2.6 mm/min	
5.	2.6 mm/min	
6.	Tungsten electrode	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT