RAMLLOY PA917G6

Polyamide 66 + PP

Polyram Ram-On Industries

Message:

30% GLASS FIBER REINFORCED PA66/PP ALLOY WITH REDUCED WATER ABSORBTION, DIMENSION STABILITY AND UV STABILIZED FOR INJECTION MOULDING APPLICATIONS.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	UV Stabilizer		
Features	Good Dimensional Stability		
	Good UV Resistance		
	Low to No Water Absorption		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow	0.30 to 0.50	%	ASTM D955
	0.30 to 0.50	%	ISO 2577
Water Absorption			
Saturation	3.0	%	ASTM D570
Saturation, 23°C	3.0	%	ISO 62
Equilibrium, 23°C, 50% RH	1.2	%	ASTM D570, ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	145	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	3.0	%	ASTM D638, ISO 527-2
Flexural Modulus	5700	MPa	ASTM D790, ISO 178
Flexural Strength	195	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	130	J/m	ASTM D256
23°C	13	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Maximum Use Temperature - Short Peaks Operation	150	°C	
Maximum Continuous Use Temperature	80	°C	
Melting Temperature	256	°C	ISO 11357-3, ASTM D3418

Flammability	Nominal Value	Test Method
Flame Rating (3.00 mm)	НВ	UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

