

TROSIFOL® Solar R40 Ultra White

Polyvinyl Butyral
Kuraray Co., Ltd.

Message:

TROSIFOL® Solar R40 Ultra White is a Polyvinyl Butyral (PVB) material. It is available in Asia Pacific, Europe, or North America.

General Information			
Appearance	White		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	DIN 53479
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	70		
Films	Nominal Value	Unit	Test Method
Tensile Strength	> 23.0	MPa	ISO 527-3
Tensile Elongation (Break)	> 250	%	ISO 527-3
Adhesion to Glass ¹	> 16.0	MPa	
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	2.0E-4	cm/cm/°C	ISO 11359-2
Specific Heat	1850	J/kg/°C	ISO 11357-4
Thermal Conductivity	0.22	W/m/K	EN 12664
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ² (23°C)	1.0E+14	ohms · cm	IEC 60093
Optical	Nominal Value	Unit	Test Method
Transmittance ³	< 1.0	%	EN 410
NOTE			
1.	Compressive Shear Strength		
2.	At 0.5% H2O content		
3.	LSG made of 2 x 3 mm low-iron glass		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT