

# Kingfa FRHIPS-1162

High Impact Polystyrene

Kingfa

Message:

Kingfa FRHIPS-1162 is a High Impact Polystyrene material. It is available in Asia Pacific or North America.

Important attributes of Kingfa FRHIPS-1162 are:

Flame Rated

Flame Retardant

Impact Resistant

Typical applications include:

Automotive

Housings

General Information			
UL YellowCard	E171666-225769		
Features	Flame Retardant		
	High Impact Resistance		
Uses	Automotive Applications		
	Housings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (23°C, Injection Molded)	27.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break, 23°C, Injection Molded)	45	%	ASTM D638
Flexural Modulus <sup>3</sup> (23°C, Injection Molded)	2250	MPa	ASTM D790
Flexural Strength <sup>4</sup> (23°C, Injection Molded)	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	78.0	°C	ASTM D648
Vicat Softening Temperature	99.0	°C	ASTM D1525 <sup>5</sup>
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-2		
3.00 mm	V-2		
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		
5.	Rate B (120°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

