

NORYL GTX™ GTX678 resin

Polyphenylene Ether + PS + Nylon

SABIC Innovative Plastics

Message:

NORYL GTX678 resin is a high performance blend of PPE/PA that exhibits an excellent balance on non-halogenated flame retardance, conductivity, ductility, and high-heat resistance. This grade can be electro-statically painted or powder coated without the need for a conductive primer.

General Information	
Features	Conductivity
	Sprayable
	Heat resistance, high
	Halogen-free
	ductility
	Flame retardancy

Processing Method	Profile extrusion molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	7.8	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/5.0 kg)	7.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	1.3 - 1.5	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	4.0	%	ISO 62
Equilibrium, 23°C, 50% RH	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2900	MPa	ASTM D638
--	2900	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	58.0	MPa	ASTM D638
Yield	58.0	MPa	ISO 527-2/50
Fracture ³	52.0	MPa	ASTM D638
Fracture	52.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	7.0	%	ISO 527-2/50
Fracture ⁵	12	%	ASTM D638
Fracture	12	%	ISO 527-2/50

Flexural Modulus			
50.0mm span ⁶	2600	MPa	ASTM D790
-- ⁷	2600	MPa	ISO 178
Flexural Stress			
--	95.0	MPa	ISO 178
Yield, 50.0mm span ⁸	95.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	12	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	70	J/m	ASTM D256
23°C	100	J/m	ASTM D256
-30°C ¹⁰	7.0	kJ/m ²	ISO 180/1A
23°C ¹¹	10	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	60.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	195	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹²	191	°C	ISO 75-2/Bf
Vicat Softening Temperature			
--	198	°C	ASTM D1525 ¹³
--	197	°C	ISO 306/B50
--	195	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	7.8E-5	cm/cm/°C	ASTM E831
Flow: 23 to 60°C	8.3E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	8.0E-5	cm/cm/°C	ASTM E831
Lateral: 23 to 60°C	8.5E-5	cm/cm/°C	ISO 11359-2
Specific Heat	1400	J/kg/°C	ASTM C351
Thermal Conductivity	0.20	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+3	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm, Testing by SABIC	V-1		UL 94

V-0

5VB

2.00 mm, Testing by SABIC

5VA

UL 94

Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
--	-----	----	----------------

Glow Wire Ignition Temperature (1.00 mm)	800	°C	IEC 60695-2-13
--	-----	----	----------------

Injection	Nominal Value	Unit
Drying Temperature	93.3 - 107	°C
Drying Time	3.0 - 4.0	hr
Drying Time, Maximum	8.0	hr
Suggested Max Moisture	0.070	%
Suggested Shot Size	30 - 50	%
Rear Temperature	260 - 299	°C
Middle Temperature	266 - 299	°C
Front Temperature	271 - 299	°C
Nozzle Temperature	277 - 299	°C
Processing (Melt) Temp	277 - 299	°C
Mold Temperature	65.6 - 93.3	°C
Back Pressure	0.345 - 1.38	MPa
Screw Speed	20 - 100	rpm
Vent Depth	0.013 - 0.038	mm

Extrusion	Nominal Value	Unit
Drying Temperature	105 - 110	°C
Drying Time	8.0	hr
Suggested Max Moisture	0.030	%
Cylinder Zone 1 Temp.	245 - 260	°C
Cylinder Zone 2 Temp.	245 - 260	°C
Cylinder Zone 3 Temp.	245 - 260	°C
Cylinder Zone 4 Temp.	245 - 260	°C
Adapter Temperature	245 - 260	°C
Melt Temperature	245 - 260	°C
Die Temperature	245 - 260	°C
Calibration Temp, First	35.0 - 75.0	°C

Extrusion instructions

Drying Time (Cumulative): 24 hrsWater Bath Temperature: 35 - 50 °C

NOTE	
1.	5.0 mm/min
2.	Type 1, 50mm/min

3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

