

Starex WX-9310UV

Acrylonitrile Styrene Acrylate

SAMSUNG SDI CO., LTD.

Message:

Heat resistant ASA that is applied to the interior/exterior material of automobile

General Information			
Features	Medium Heat Resistance		
Uses	Automotive Exterior Parts		
	Automotive Interior Parts		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow : 3.20 mm	0.45	%	ASTM D955
Across Flow : 3.20 mm	0.50	%	ASTM D955
Across Flow : 3.20 mm	0.45	%	ISO 2577
Flow : 3.20 mm	0.50	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	105		ASTM D785
R-Scale	106		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1900	MPa	ASTM D638
--	2200	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	44.0	MPa	ASTM D638
Yield	49.0	MPa	ISO 527-2/50
Break ³	36.0	MPa	ASTM D638
Break	37.0	MPa	ISO 527-2/50
Tensile Elongation			
Break ⁴	12	%	ASTM D638
Break	12	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	2200	MPa	ASTM D790
-- ⁶	2400	MPa	ISO 178
Flexural Strength			

-- ⁷	67.0	MPa	ASTM D790
-- ⁸	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	14	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	180	J/m	ASTM D256
23°C, 6.35 mm	88	J/m	ASTM D256
23°C ¹⁰	16	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 6.40 mm	97.0	°C	ASTM D648
0.45 MPa, Unannealed, 4.00 mm	96.0	°C	ISO 75-2/B
0.45 MPa, Annealed	106	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	90.0	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	80.0	°C	ISO 75-2/A
1.8 MPa, Annealed, 4.00 mm	102	°C	ISO 75-2/A
Vicat Softening Temperature			
--	101	°C	ISO 306/B50
--	103	°C	ISO 306/B120
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0 to 90.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	180 to 190	°C	
Middle Temperature	200 to 210	°C	
Front Temperature	220 to 230	°C	
Nozzle Temperature	240	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	49.0 to 245	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		

7.	2.8 mm/min
8.	2.0 mm/min
9.	Thickness: 4 mm
10.	Thickness: 4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

