

Plexiglas® V920

Polymethyl Methacrylate Acrylic
Altuglas International of Arkema Inc.

Message:

Plexiglas® V920 is a General-purpose thermoplastic acrylic resin formulated for injection molding and extrusion applications. It is characterized by its very high melt flow. Plexiglas® V920 has excellent weatherability and optical properties allowing it to excel in applications requiring outdoor stability, high quality surface appearance and/or precision optics. Plexiglas® V920 is easy to process due to its exceptional thermal stability, extrusion melt strength, and excellent tool surface reproduction and release properties. Supplemental moldflow simulation data is available. It has excellent resistance to many chemicals including solutions of inorganic acids, alkalis and aliphatic hydrocarbons such as VM&P naphtha and heptane. Additionally, it is virtually unaffected by a wide range of commercial products including many beverages, foodstuffs, detergent solutions and cleaners.

General Information			
UL YellowCard	E39437-231440	E39437-231441	
Features	BPA Free		
	Good Color Stability		
	Good Dimensional Stability		
	Good Thermal Stability		
	Good UV Resistance		
	Good Weather Resistance		
	High Clarity		
	High Scratch Resistance		
	Low Shrinkage		
Uses	Automotive Applications		
	Consumer Applications		
	Optical Applications		
Agency Ratings	FDA 21 CFR 177.1010		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
	Colors Available		
	Opaque		
	Translucent		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D955

Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ASTM D638
Tensile Strength (Yield)	68.9	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3100	MPa	ASTM D790
Flexural Strength (Yield)	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	16	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ¹			ASTM D648
0.45 MPa, Annealed	92.8	°C	
1.8 MPa, Annealed	90.6	°C	
Vicat Softening Temperature			
--	100	°C	ASTM D1525 ²
--	91.1	°C	ASTM D1525 ³
Thermal Conductivity	0.19	W/m/K	ASTM C177
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index ⁴	1.490		ASTM D542
Transmittance (3180 µm)	92.0	%	ASTM D1003
Haze (3180 µm)	< 1.0	%	ASTM D1003
Additional Information	Nominal Value		Test Method
ASTM Classification	PMMA 0121V4		ASTM D788
Injection	Nominal Value	Unit	
Drying Temperature	79.4 to 87.8	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50	%	
Suggested Max Regrind	20	%	
Rear Temperature	204	°C	
Middle Temperature	210	°C	
Front Temperature	216	°C	
Nozzle Temperature	210	°C	
Processing (Melt) Temp	< 271	°C	
Mold Temperature	65.6 to 85.0	°C	
Injection Rate	Fast		
Back Pressure	0.689	MPa	
Screw Speed	50 to 100	rpm	

Screw L/D Ratio	15.0:1.0 to 20.0:1.0	
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	
Vent Depth	0.051	mm

NOTE		
1.	Annealing cycle: 4hrs @ 176°F	
2.	Rate A (50°C/h), Loading 1 (10 N)	
3.	Rate A (50°C/h), Loading 2 (50 N)	
4.	ND @ 72°F	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT