

LNP™ THERMOCOMP™ ZF006 compound

Polyphenylene Ether + PS

SABIC Innovative Plastics

Message:

LNP THERMOCOMP ZF006 is a compound based on PPE+PS Blend resin containing Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound ZF-1006

Product reorder name: ZF006

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage - Flow (24 hr)	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	9870	MPa	ASTM D638
Tensile Strength (Break)	108	MPa	ASTM D638
Tensile Elongation (Break)	1.6	%	ASTM D638
Flexural Modulus	8910	MPa	ASTM D790
Flexural Strength	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Unnotched Izod Impact (23°C)	530	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	136	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Rear Temperature	277 - 288	°C	
Middle Temperature	288 - 299	°C	
Front Temperature	299 - 310	°C	
Processing (Melt) Temp	299 - 304	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT