# Sumitomo PP AV161

### Polypropylene Copolymer Sumitomo Chemical Asia

#### Message:

Applications For general purpose applications such as houseware, furniture, battery cases, crates, containers, chair, toys, and detergent pails, etc. Characteristics Medium flow, high impact, high stiffness, and high heat stability.

General Information				
Features	Block Copolymer			
	High Heat Resistance			
	High Impact Resistance			
	High Stiffness			
	Medium Flow			
Uses	Battery Cases			
	Containers			
	Crates			
	Furniture			
	General Purpose			
	Household Goods			
	Pails			
	Toys			
	Toys			
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.900	g/cm³	ASTM D792A	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238	
Molding Shrinkage			Internal Method	
Across Flow	1.4	%		
Flow	1.4	%		
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness	90		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
Yield	25.0	MPa		
Break	13.0	MPa		
Flexural Modulus	1170	MPa	ASTM D790A	
Impact	Nominal Value	Unit	Test Method	

Notched Izod Impact Strength			ASTM D256
-20°C	4.0	kJ/m²	
23°C	10	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (	0.45		
MPa, Unannealed)	106	°C	ASTM D648
Vicat Softening Temperature	154	°C	ASTM D1525 <sup>1</sup>
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	20.0 to 70.0	°C	
Mold Temperature  NOTE	20.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

